

What is claimed is:

1. A photocurable and antistatic resin composition for coating an optical fiber,
comprising (A) a photopolymerizable urethane acrylate oligomer, (B) a
5 reactive monomer having at least one (meth)acrylate or vinyl group, (C)
a photoinitiator, and (D) an antistatic agent compatible with the oligomer
and the monomer.
2. The resin composition of claim 1, wherein the components (A) to (D) are
10 employed in amounts of 40 to 70 % by weight, 15 to 50 % by weight, 0.5
to 10 % by weight, and 1 to 30 % by weight, respectively, based on the
total weight of the composition.
3. The resin composition of claim 1, which further comprises (E) a pigment
15 or dye.
4. The resin composition of claim 3, wherein the pigment or dye is employed
in an amount of 1 to 10 % by weight of the total resin composition.
- 20 5. The resin composition of claim 1, wherein the photopolymerizable
urethane acrylate oligomer (A) is synthesized by an urethane reaction
from a mixture comprising (i) 25 to 50% by weight of a polyol
copolymer optionally mixed with a sorbitan fatty acid ester or
polyoxyethylene sorbitan fatty acid ester, (ii) 20 to 40 % by weight of a
25 polyisocyanate, (iii) 20 to 35 % by weight of a hydroxy(meth)acrylate,
(iv) 0.01 to 1 % by weight of an urethane reaction catalyst and (v) 0.01
to 1 % by weight of a polymerization initiator.

6. The resin composition of claim 5, wherein the sorbitan fatty acid ester is selected from the group consisting of sorbitan monolaurate, sorbitan monopalmitate, sorbitan monostearate, sorbitan tristearate, sorbitan monooleate, sorbitan sesquioleate, sorbitan trioleate, and a mixture thereof.
7. The resin composition of claim 5, wherein the sorbitan fatty acid ester is employed in an amount of 1 to 5 % by weight of the polyol polymer.
8. The resin composition of claim 1, wherein the antistatic agent is selected from the group consisting of a non-ionic or cationic amine, a polyhydric alcohol fatty acid ester, a fatty amide, an alkyl betain and a mixture thereof.